cameleo®
DECO COATINGS

PRODUCT TECHNICAL DATA SHEET

CEMFILLER (for floors)

Microcement

DESCRIPTION:	A product based on polymer-modified white cement.
COLOUR:	White/cream-coloured base.
COLOURING METHOD	Can be tinted with Cameleo pigments.
SUBSTRATE PREPARATION:	Before applying a Cameleo decorative effect, prepare the substrate surface properly. - Concrete substrates Concrete substrates must be allowed to cure for at least 30 days and their moisture content must not exceed 4%. The concrete substrate strength class must be at least C20/25 (B25). Remove all contamination and dirt mechanically. Apply one coat of CAMEPRIMER P3000 to the substrate prepared in this way.
PRODUCT PREPARATION:	Pour the contents of the container into the appropriate amount of water (25% water per 1 kg, equivalent to 5 l of water/resin per 20 kg container). Mix thoroughly using a mechanical mixer. When tinting the compound, disperse the pigment in the mixing water, then add the contents of the container and mix mechanically. Use the product within 2 h of mixing with water. When working on areas larger than the coverage of a single container, combine and mix the contents of the individual containers in one larger container.
APPLICATION:	Flexible Venetian trowel. Maximum layer thickness: 10 mm.
TECHNICAL INFORMATION:	Thinner - Water Specific gravity - 1.79 g/cm³ (water content: 30%) Consumption - Up to 1.25 kg/m² of dry product at 1 mm layer thickness Practical consumption - Consumption depends on factors such as substrate porosity and roughness and material losses during application. pH - Approx. 8.2 ± 10% (water content: 30%)
RECOMMENDED PRIMERS	CAMEPRIMER P100, CAMEPRIMER P3000
TOOL CLEANING:	Warm soapy water.

SURFACE CLEANING AND MAINTENANCE	The surface may be washed 7 days after completion of the full application process. Do not use detergents. Clean with soapy water.
PRODUCT DRYING TIME:	At 20°C and 50% air humidity: Touch dry - 8-12 h after application. Cured - 48 h after application.
APPLICATION CONDITIONS:	Application temperature: +10°C to +30°C. Minimum substrate temperature: +10°C. Maximum substrate temperature: +30°C. Substrate moisture content must not exceed 4%. Maximum air humidity: 75%.
STORAGE AND TRANSPORT:	Store in a tightly closed container at +5°C to +25°C. The product is frost-sensitive. Protect from sunlight. Shelf life: 12 months from the date of manufacture in the original sealed container (date of manufacture on the container).
PACK SIZES:	8 kg, 20 kg
SAFETY INSTRUCTIONS:	All product safety instructions are available in the Safety Data Sheet for the chemical substance (mixture).
NOTES:	Mix the product thoroughly by hand before use. When working on areas larger than the coverage of a single container, the contents of the individual containers must be mixed together in one larger container. The colours shown in the catalogue may differ from the actual colours on the wall. Colours depend on the application method, texture, gloss, lighting, sunlight, and the types and intensity of other colours in the surroundings. Storage, transport and application conditions, as well as the final effect, are beyond our control and therefore cannot constitute a guarantee in the legal sense. Statutory provisions and any third-party rights must be observed in all cases.
WARRANTY:	Cameleo Leśniewicz Gradkowska Spółka Jawna warrants that Cameleo products are of merchantable quality and comply with the standards declared by Cameleo. Cameleo products are covered by warranty provided that they are used in accordance with the instructions in the Product Technical Data Sheets and Decorative Effect Technical Data Sheets. Products are not covered by warranty if they are not used in accordance with the information in the Product Technical Data Sheets and Decorative Effect Technical Data Sheets. Liability under this warranty, if the product proves defective, is limited exclusively to replacement of the product or a refund of its purchase price. This warranty is valid for one year from the date of purchase of the product.

MANUFACTURER:	CAMELEO Leśniewicz Gradkowska Spółka Jawna, ul. Sikorskiego 139, 63-100 Psarskie. Tel. 61-28-35-899